

Epoxy Resin Systems



Resin Selector Guide

- Resin Systems
- Polyester Gelcoat Resins





RESIN	HARDENER	ULTIMATE Tg (°C)	VISCOSITY (mpa·s @25°C)	POT LIFE (MINS)	THIN FILM GEL TIME @25°C)	CURE CYCLE	POST CURE	STORAGE LIFE -18°C	20-25°C	PROCESSING METHOD	APPLICATIONS
RESIN SYSTEMS											
RS-L135	RS-H133 RS-H135 RS-H136 RS-H137 RS-H138	85 - 90	500 - 1000	25 - 720	4 - 20 hours	24 hours @ 25°C	10 hours @ 80°C	n/a	12 months	Wet layup, filament winding, Pressure moulding, pultrusion, vacuum bag moulding.	Boats and shipbuilding, wind energy turbine blades, sports equipment, models.
RS-M135	RS-MH134 RS-MH137	90 - 95	200 - 250	20 - 240	-	24 hours @ 25°C	10 hours @ 70°C	n/a	12 months	Injection moulding, vacuum infusion, pultrusion.	Boats and shipbuilding, wind energy turbine blades, sports equipment.
RS-M235	RS-MH235 RS-MH236 RS-MH237 RS-MH238	85 - 95	200 - 250	10 - 600	3 - 24 hours	24 hours @ 25°C	15 hours @ 80°C	n/a	12 months	Injection moulding, vacuum infusion, pultrusion.	Rotor blades for wind turbines, boat and shipbuilding, sports equipment, model construction, tooling and moulding.
RS-L285	RS-H285 RS-H286 RS-H287	100 - 105	300 - 500	40 - 260	2 - 6 hours	24 hours @ 25°C	15 hours @ 80°C	n/a	12 months	Wet layup, filament winding, pressure moulding, injection moulding, vacuum infusion moulding, pultrusion, vacuum bag moulding.	Gliders, motorgliders, boats automotive, sports equipment, and other high performance products, low temperature moulds & tools.
RS-L418	RS-H418	120 - 125	600 - 800	180 - 240	5 - 6 hours	24 hours @ 25°C	20 hours @ 100°C	n/a	12 months	Wet layup, filament winding, pressure moulding, vacuum infusion moulding, pultrusion, vacuum bag moulding.	Gliders and motorgliders, powered aircraft and helicopters, boats and automotive, mould and jig construction, sports equipment and other high performance products.
RS-L485	RS-H485 RS-H486 RS-H487	125 - 145	300 - 600	10 - 150	-	6 hours @ 45°C	3 hours @ 120°C	n/a	12 months	Wet layup, vacuum infusion, vacuum bag moulding.	Applications that require high heat resistance, aerospace, automotive, tooling and moulding.
Flexibiliser RS-V51	-	-	30 - 80	-	-	-	-	-	12 months	For use in epoxy systems to increase the flexibility of the cured resin.	-
POLYESTER GELCOAT RESINS											
RS-T30 / RS-T35	RS-SF10 / RS-SF2	-	-	30 - 45	100 - 150 minutes	5 - 6 hours @ 25°C	2 - 3 days @ 25°C	6 months	3 months	Spraying, brushing, rolling, blade coating.	Aircraft, automotive, model making.

Find out what PRF can do for your business

Make an enquiry today at:

t: +44 (0) 1202 680022

e: enquiries@prfcomposites.com

www.prfcomposites.com

PRF Composite Materials

3 Upton Road

Poole

Dorset BH17 7AA

Important Notice

All statements, technical information and recommendations offered are only for consideration and evaluation. Whilst they are believed to be accurate they are not guaranteed and are provided without warranty of any kind. No undertaking is given that the goods/products supplied are fit for its particular purpose. The buyer/user shall assume all risks and liabilities in connection therewith.

Resin Selector Guide ed. 1.3 Jul 2015



Prepreg



Reinforcements



Resin



Aerospace Adhesives



Shears



Tooling Block



Mould Release



Consumables