

# Product Data

## Prepreg Systems



### Medium Temperature Cure Resin System

## RP542-3

90°C - 120°C Cure

### PROVISIONAL DATA

#### Applications

- Aerospace
- Automotive
- Motorsport Components
- Marine
- Defence

#### Processing Methods

- Vacuum bag
- Autoclave
- Press moulding
- Tube rolling
- Pressure bag





## Introduction

RP542-3 is a winter version of our popular RP542-1 component prepreg, providing a controlled flow, toughened epoxy prepreg system formulated for the manufacture of high performance structural composite parts requiring very good impact strength properties. The system has been formulated for a medium temperature cure of 90 - 120°C under vacuum or autoclave pressure and is also suitable for press moulding. Fully cured, this system has a dry service temperature capability up to 120°C. The component surface finish with this system is excellent.

The high tack level of this system is ideal for use in cold weather conditions, where temperatures in workshops drop below 15°C. The out life of the system is up to 40 days at 20°C, making this system suitable for the manufacture of large composite components.

RP542-3 can be supplied on most of the vast range of PRF reinforcement materials in widths up to 1350 mm wide.

## Main Features

- Toughened system
- Excellent surface finish
- Core bondable
- Standard Cure 90°C - 120°C
- Service Temperature up to 120°C
- Controlled flow system
- Out life 40 days at room temperature
- Available on most of PRF's reinforcement fabrics

## Storage

This product should be stored in refrigerated conditions.

Out life: 40 days at 20°C.

Shelf life is 6 months at below -5°C or 12 months at below -18°C.

**Health and Safety** - Refer to the full Material Safety Datasheet before use.



## Processing

RP542-3 prepreg resin system may be processed at room temperature using established prepreg moulding techniques on properly prepared moulds. The cure cycle depends on the construction of the component and processing method. If honeycomb core is used in the part, the temperature ramp should be increased at a slower rate to enable a controlled flow of the resin to form a fillet between the core and skin.

Recommended cure cycle is to ramp from ambient to 110°C at 1-2°C/minute and then dwell for 2 hours. Part should then be allowed to cool naturally before demoulding.

Alternative cure temperatures and times are given in the table below:

## Cure cycles

### Laminates with honeycomb core

Elevate temperatures at 2 - 5°C per minute up to 110°C. Hold the final temperature for 2 hours then allow the component to cool naturally inside the oven/autoclave before demoulding.

### Vacuum bagged monolythic laminates

Elevate temperature at 3 - 5°C per minute up to 110°C, hold for 2 hours then allow the component to cool naturally inside the oven/autoclave before demoulding.

### Press moulded monolythic laminates

RP-542-1 system may be applied directly to hot press moulds at temperatures up to 130°C.

The cure time at the highest temperature will be approximately 45 minutes. The mould and component temperatures should be cooled to below 80°C before demoulding. It is important, when manufacturing honeycomb sandwich panels without the use of adhesive films, to increase the resin content on the fabric plies being used as the first layers against the honeycomb. This ensures enough resin is available for the formation of the resin fillet between the honeycomb and the skins.

## Post cure cycle

TEMPERATURE (°C)	120
TIME (hours)	1

A post cure can be carried out if the maximum T<sub>g</sub> is required. The recommended post cure cycle is to ramp the temperature to 120°C at 1-2°C/minute and hold for 1 hour.

## Mechanical Properties

To be confirmed once testing is complete.

# Find out what PRF can do for your business

Make an enquiry today at:

t: +44 (0) 1202 680022

e: [enquiries@prfcomposites.com](mailto:enquiries@prfcomposites.com)

[www.prfcomposites.com](http://www.prfcomposites.com)

## PRF Composite Materials

3 Upton Road

Poole

Dorset BH17 7AA

### Important Notice

All statements, technical information and recommendations offered are only for consideration and evaluation. Whilst they are believed to be accurate they are not guaranteed and are provided without warranty of any kind. No undertaking is given that the goods/products supplied are fit for its particular purpose. The buyer/user shall assume all risks and liabilities in connection therewith.

RP542-3 ed. 1.0 Mar 2017

Plastic Reinforcement  
Fabrics Ltd



Prepreg



Reinforcements



Resin



Aerospace  
Adhesives



Shears



Tooling Block



Mould Release



Consumables