## Prepreg Systems Selector Guide



| RESIN<br>SYSTEM                | PRODUCT | CURE<br>TEMP. (°C) | Tg (°C)                                  | SHELF LIFE<br>@ 20°C                          | REINFORCEMENT         | APPLICATION  |
|--------------------------------|---------|--------------------|--|---|-----------------------|--|
| TOOLING PREPRI                 | EG .    |                    |  |   |                       |  |
| Ероху                          | RP800   | 50 - 180           | 190 DSC                                  | Tack life: 4 - 5 days<br>Out life: 5 - 6 days | Woven fabrics         | Tooling structures   |
| Ероху                          | RP801   | 60 - 180           | 190 DSC                                  | Tack life: 5 days<br>Out life: 7 days         | Woven fabrics         | Tooling structures   |
| Ероху                          | RP802   | 60 - 180           | 190 DSC                                  | Tack life: 10 days<br>Out life: 12 days       | Woven fabrics         | Tooling structures   |
| Ероху                          | RP803   | 60-180             | 190 DSC                                  | Tack life: 7 days<br>Out life: 9 days         | Woven fabrics         | Tooling structures   |
| COMPONENT PR                   | EPREG   |                    |  |   |                       |  |
| Ероху                          | RP442   | 65 - 120           | 125 DSC                                  | 30 days                                       | Woven fabrics         | General & Industrial   |
| Ероху                          | RP507   | 90 - 160           | 121 DSC                                  | 30 days                                       | Unidirectional carbon | General & Industrial parts. Fire retardant version also available. |
| Ероху                          | RP522   | 110 - 135          | 115 DSC                                  | 30 days                                       | Woven fabrics         | General & Industrial   |
| Ероху                          | RP542-1 | 80 - 120           | 125 DSC                                  | 40 days                                       | Woven fabrics         | General & Industrial   |
| Ероху                          | RP542-3 | 90 - 120           | 120 DSC                                  | 40 days                                       | Woven fabrics         | High levels of tack<br>- suitable for work<br>conditions c.15°C    |
| Ероху                          | RP548   | 90 - 120           | 121 DSC                                  | 20 days                                       | Woven fabrics         | General and Industrial   |
| Ероху                          | RP549   | 80 - 150           | 160 DMA onset<br>195 DMA peak            | 30 days                                       | Woven fabrics         | General & Industrial,<br>motorsport                                |
| Ероху                          | RP570   | 140                | 140 DSC<br>131 DMA onset<br>155 DMA peak | 40 days                                       | Woven fabrics         | Press moulding   |
| EPOXY ADHESIVE AND RESIN FILMS |         |                    |  |   |                       |  |
| RESIN<br>SYSTEM                | PRODUCT | CURE<br>TEMP. (°C) | FILM WEIGHT (g/<br>m²)                   | SHELF LIFE<br>@ 20°C                          | REINFORCEMENT         | APPLICATION  |
| F                              | DESSO   | 100 150            | 150 450                                  | 20.1  | Can be                | General industrial   |

Tg figures assume full curing.

## Important Notice

Ероху

Ероху

## All values are nominal.

All statements, technical information and recommendations offered are only for consideration and evaluation. Whilst they are believed to be accurate they are not guaranteed and are provided without warranty of any kind. No undertaking is given that the goods/products supplied are fit for its particular purpose. The buyer/user shall assume all risks and liabilities in connection therewith. Prepreg Selector Guide ed. 7.0 Oct 2017

150 - 450

125

30 days

30 days

supported by

supported by

carrier

Can be

carrier

Plastic Reinforcement Fabrics Ltd

bonding and resin

General industrial

bonding and resin

film infusion.

film infusion.







3 Upton Road, Poole, Dorset BH17 7AA, England

RF550

RF552

100 - 150

90 - 120

- t: +44 (0) 1202 680022 f: +44 (0) 1202 680077
- e: orders@prfcomposites.com

Visit: prfcomposites.com/prepreg for updates

